

SolvoPrint™ Paper 240 Satin

Product Specifications



Carrier		
Carrier Material	Heavy paper with solvent inkjet coating	
Thickness	232 ± 6 µm	9 mil nominal
Weight	219 ± 5 g/m ²	6.5 oz/yd ²
Gloss level 60°	50	Dr. Lange Reflectometer, 60°
Whiteness [Lab]	L*: 96.5 a*: 0.3 b*: 0.8	
More Information		
Storage Conditions	Original boxed at 5 - 40°C / 40 - 104°F at R.H. 30 – 90% keep dry / indoor	
Material Durability (unprinted)	12 Months	

All tests were performed in accordance with 23/50-2, DIN 50014.

Areas of Application

- Ideally suitable for photo prints, posters, graphics, etc.
- Suitable for indoor applications

Advantages / Special Features

- Very good printability and handling
- Good water and scratch resistance after complete drying
- Bright white image side
- Satin surface for low glare when used in high intensity display lighting
- Bright colors with high brilliance and photorealistic print quality
- All purpose media; very versatile

Process & Handling

- To avoid finger prints, usage of cotton gloves is recommended
- For protective purpose usage of Neschen protective laminates is recommended (ensure adequate drying before lamination) – drying time of min. 12 hours is recommended
- Must not be stored lying flat, storage is best to be done in the original box
- When hot laminating ensure that the heat is applied from both upper and lower rollers

Printability	
Water-based	
Solvent	◆
Eco Solvent	◆
UV	◆



Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.