

SolvoTex™ Artist Premium Heavy S

Product Specifications



Material Details	
Material	100% Polyester
Weight	8.5 oz/yd ² [290 g/m ²]
Thickness	12.2 mil [310 µm]
Character	Heavy canvas structure
Tear Force [N/15mm]	658/457 warp/weft
Elongation at Tear [%]	50/39 warp/weft
Tear Resistance [N/mm ²]	138/95 warp/weft
Flammability	Meets NFPA 701, B1, M1
Handling/Storage Conditions	5°F to 170°F [-20°C to 80°C]

	Art Reprographic	Indoor Banners	Outdoor Banners	POS	Tradeshow	Wall Covering
Applications	◆	◆	◆	◆	◆	◆

Printer Compatibility	
Solvent	◆
Latex	◆
UV-curable	◆

Processing & Handling

- Print slowly.
- To avoid fingerprints, it is recommended that protective gloves be worn while handling.
- To prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured).

Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.

Neschen Americas
 7091 Troy Hill Drive, Elkridge, MD 21075
 Tel: 410-540-8900
 Tech Service: 800-486-6502
 Fax: 410-579-8960

