

SolvoTex™ PVC Standard Blockout

Product Specifications



| Material Details | |
|---------------------------|---|
| Material | 100% Polyester, PVC coated on both sides |
| Weight | 15.2 oz/yd ² (520 g/m ²) |
| Thread Count (Ends/Picks) | 41/41 per inch |
| Yarn (dtex) | 550 dtex |
| Tensile Strength | 341/284 lbs/inch |
| Tear Resistance | 30/30 lbs |
| Flammability | Meets NFPA 701 Test #2 (2004 Edition), B1, M2 |
| Low Temperature | -22°F (-30°C) without cracking |
| Outdoor Durability | 18 months |
| Added Value | UV resistant, printable on both sides, true blockout, high frequency and hot air weldable |

| | Indoor Banners | Outdoor Banners | POS | Tradeshow | Pole Banners |
|--------------|----------------|-----------------|-----|-----------|--------------|
| Applications | ◆ | ◆ | ◆ | ◆ | ◆ |

| Printability | |
|--------------|---|
| Solvent | ◆ |
| Eco Solvent | ◆ |
| UV | ◆ |

Processing & Handling

- Print slowly.
- To avoid fingerprints, it is recommended that protective gloves be worn while handling.
- To prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured).

Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.

Neschen Americas
 7091 Troy Hill Drive, Elkridge, MD 21075
 Tel: 410-540-8900
 Tech Service: 800-486-6502
 Fax: 410-579-8960

