

SolvoPrint™ Daytona PVC Banner

Product Specifications



Material Details	
Material	Polyester with PVC laminated on both sides
Weight	13.7 oz/yd ² (470 g/m ²)
Thickness	14.4 mil
Yarn (dtex)	330 / 550
Ends/Picks	18 x 12 per inch
Tensile Strength	108/85 lbs/inch
Tear resistance	11/22 lbs
Adhesion	8/10 lbs/inch
Shelf Life	2 years after the production date
Storage Conditions	-20° to + 80°C (5° to 170°F)

Areas of Application

- Display Systems (Roll Up or similar)
- Tradeshow Graphics
- Point of Purchase Graphics
- Suitable for indoor and short term outdoor applications

Advantages / Special Features

- Balanced color reproduction and photorealistic print quality
- Quick drying with normal ink load
- Part of Neschen's INDISPLAY solutions

Process & Handling

- To avoid fingerprints, it is recommended that protective gloves be worn while handling.
- To prevent problems after printing, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured).

Printability	
Solvent	◆
Eco Solvent	◆
UV	◆



Temperatures and thicknesses are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. The purchaser should test material to determine if it is suitable for their own specific purpose.